

O-Ring Compatibility Chart

	Viton	Silicone	Buna-N	FETFE	Ethylene Propylene	CAPFE	Kalrez	Chemraz
Alcohols	E	E	F-G	E	G-E	E	E	E
Aldehydes	P	F	P	E	F	E	E	E
Aliphatic Hydrocarbons	E	P-G	E	E	P	E	E	E
Ammonia	E	E	G	E	G	E	E	E
Aromatics	E	P	P	E	P	E	E	E
Chlorinated Hydrocarbons	E	P	F-P	E	P	E	E	E
Concentrated Bases	E	E	G	E	E	E	E	E
Concentrated Mineral Acids	F-G	P	G	E	E	E	E	E
Ether THF	P	E	P	P	G	E	E	E
Fuel Oils	E	F	E	E	P	E	E	E
Ketones	P	P	P	P	G-E	E	E	E
Compression Set	E	G-E	G	E	G-E	P	E	E
Temperature Limits° C	-23 TO 204	-62 TO 260	-54 TO 121	-23 TO 240	-54 TO 149	-73 TO 204	-37 TO 260	-20 TO 232
KEY: E=EXCELLENT P=POOR; G=GOOD; F=FAIR								